

UNICHEM PAB – A 60 SS

SLOW SETTING ANIONIC BITUMEN EMULSION

UCA-WP-09-0722

DESCRIPTION

UNICHEM PAB – A 60 SS is an anionic type asphaltic emulsion & further characterized by their ability to remain stable on storage, although produced with equipment that generates a wide range of shearing forces.

UNICHEM PAB – A 60 SS is cold liquid applied water proofing bitumen emulsion. The product is made using a process in which special grade of bitumen, emulsifier & other additive have been gone through a high share rate colloid mill & the properties of bitumen have direct effect on bitumen emulsion.

The slow - setting emulsions are grades of emulsion that are sufficiently stable to allow mixing with fine or dusty aggregate mineral particles and further processing before setting.

USES

- ❖ Multipurpose waterproofing & damp proofing of concrete, asbestos cement panels, wood, protection of steelwork, pipes & metal.
- ❖ Can be used below or above ground level for application in concrete, masonry, metal & asphalt surfaces.

ADVANTAGES

- Solvent free, cold applied, no heating required
- Active adhesion, binder for dust particles
- Simple & Easy to use, brush applied
- Economical, non-hazardous, non-flammable
- Chemically reacts with Portland cement constituents forming a water – insoluble salt & thus possess valuable water-resistant characteristics.

TYPICAL PROPERTIES

APPEARANCE	DARK BROWN LIQUID
SPECIFIC GRAVITY	0.99 - 1.01 @ 25 °C.
PARTICLE CHARGE	NEGATIVE
VISCOSITY @25°C	20 - 100
RESIDUE %	57 – 60 (DISTILLATION)
SOLUBILITY IN TRICHLOROETHYLENE%	97 - 98
PENETRATION @ 25°C	100 - 200
COVERAGE	2.5- 3.5 m ² /Ltr for two coats will give 200 - 300 microns DFT.* *Coverage rates vary on the Porosity and texture of the concrete to be treated
PACKAGING	20, 200 LITRE. Other packaging sizes are available upon request

STANDARDS

UNICHEM PAB A 60 SS complies with ASTM D 977

INSTRUCTIONS FOR USE

SURFACE PREPARATION

The surface must be clean & free of oil, grease or other foreign matters.

Free the surface of laitance, loose dust particles, oil, grease and other dirt. Oil or grease can be removed by using a strong industrial detergent or organic degreaser. Wire brush and broom the surface before application. In some cases, the existing concrete may have to be chipped to get to the original, sound substrate.

UNICHEM PAB – A 60 SS

SLOW SETTING ANIONIC BITUMEN EMULSION

UCA-WP-09-0722

APPLICATION

UNICHEM PAB – A 60 SS should be stirred well before application. It can be applied by brush, roller or spray equipment. It should be allowed to dry naturally.

Two or more coats must be applied to ensure a good n durable finish. The gap between two coats must be 3 – 4 hours once previous coats have fully dried.

CLEANING

UNICHEM PAB – A 60 SS can be removed from equipment & tools with water & any suitable solvent like gasoline or kerosene.

STORAGE & SHELF LIFE

UNICHEM PAB – A 60 SS should be protected from extremes of temperature. Store in dry & shaded area in original packaging. The container should be kept covered during working in order to prevent evaporation. Minimum 6 months if stored unopened in the original packaging

Note: It is advised to mix well if stored for prolonged periods.

SAFETY PRECAUTIONS

Personal should use & wear protective mask, gloves, goggles during application.

Care must be taken to ensure that there is adequate ventilation. Fires & naked flames are kept away from storage & application area.

LIMITATION OF LIABILITY

This information is based on our current level of knowledge. It is given in a good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.

P.O BOX 80071
BUILDING 1928
ROAD 5146, BLOCK 951
ASKAR, KINGDOM OF BAHRAIN

PHONE : +973 17830830
info@unichembahrain.com
www.unichembahrain.com
CR No. 51803